

OPN-CHEMIE GmbH

Produktion techn. Aerosole - Sprays

In der Au 14, D-57290 Neunkirchen / Germany

Phone: +49 (0) 27 35 / 77 25-0 Fax: +49 (0) 27 35 / 77 25-90

www.opn-chemie.com info@opn-chemie.de



Product Information

OPN-Long Term Primer "Rust Stop"

AUBURN

tested according to:

DIN 53151: cross cut test

DIN 53167: salt spray test

DIN 53152: mandrel bending test

Properties:

- paintable - after previous test
- prevents from further corrosion
- produces smooth, non porous surface, when used properly
- fast drying
- heat resistant up to about +80°C, short term up to about +120°C

Application Range:

- reliable anti corrosion primer

Application:

Our information are recommendations based on our experience. We accept no liability for any damage without tests concerning suitability for the specific application, without preliminary trials and if the products is misused. Can should have room temperature and **only be sprayed at good ventilated areas**. Shake can strongly for 2 minutes before every spraying process until the stirring ball is free. **Try and test on similar surface for material compatibility**. Remove rust and degrease the surface thoroughly and spray crosswise at a distance of 25 to 30 cm. In case of several layers let it dry for 5 minutes before spraying the next layer.

Self cleaning nozzle.

Only for professional use! Always observe safety data sheet before use.

Delivery information:

Art.-No. 66410 Spray: 400 ml Content, Packing Unit: 12 Cans/Carton

Observe the information on the label and of the EC-safety data sheet!

Our technical information has been compiled carefully to the best of our knowledge. Because of the many possible influences during processing and use of the products they do not relieve the processor of its own, conscientious exams! A legally binding assurance of certain properties or of the suitability for a particular purpose can not be derived from our information. Existing laws and regulations must be checked and observed from the processor of our products before use in his own responsibility.

All text passages are subject to the copyright of OPN-CHEMIE GmbH.